

## **TECHNICAL DATASHEET**

SAP No. 30007517 Article Description Y-E-1199g/m<sup>2</sup>-1270mm

Textile Structure 7005232 SAERTEX®

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)									
Layer	Construction	Areal weight	Tolerance	Material					
3	0°	709 g/m²	+/- 5,0 %	E-glass 2.400 TEX					
2	45 °	242 g/m²	+/- 5,0 %	E-glass 300 TEX					
1	-45 °	242 g/m²	+/- 5,0 %	E-glass 300 TEX					
Stitching		6 g/m²	+/- 1 g/m²	PES [Polyester] 76 dtex					

Fiber input can be determined individually

FURTHER CHARACTERISTICS									
Gauge	5,0	Stitching pattern	tricot-warp	Width (nominal)	1270 mm				
Stitch length	2,60 mm	Total tolerance	+/- 5,1 %	Total areal weight	1199 g/m²				
<b>9</b> \		Every roll is equipped the foil or on the box.		core. A further label is located	outside on				

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging

options can be determined individually.

Storage Keep in original packaging. Store in a dry environment. Avoid direct sunlight. (recommendation) Fabrics to be kept under processing conditions at least 24 hours

prior to use to avoid problems with humidity and electrostatic charge.