

## TECHNICAL DATASHEET

SAP No. 30007629 Article Description X-E-996g/m<sup>2</sup>-1270mm

Textile Structure 7005052 SAERTEX<sup>®</sup>

### ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

| Layer     | Construction | Areal weight         | Tolerance              | Material  |
|-----------|--------------|----------------------|------------------------|-----------|
| 3         | 45 °         | 494 g/m <sup>2</sup> | +/- 5,0 %              | E-glass   |
| 2         | 0 °          | 2 g/m <sup>2</sup>   | +/- 5,0 %              | E-glass   |
| 1         | -45 °        | 494 g/m <sup>2</sup> | +/- 5,0 %              | E-glass   |
| Stitching |              | 6 g/m <sup>2</sup>   | +/- 1 g/m <sup>2</sup> | synthetic |

Fiber input can be determined individually

### FURTHER CHARACTERISTICS

|               |         |                   |           |                    |                      |
|---------------|---------|-------------------|-----------|--------------------|----------------------|
| Gauge         | 5,0     | Stitching pattern | warp      | Width (nominal)    | 1270 mm              |
| Stitch length | 2,60 mm | Total tolerance   | +/- 5,1 % | Total areal weight | 996 g/m <sup>2</sup> |

**Labelling (Standard)** Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

**Packaging (Standard)** Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

**Storage** With original packaging: No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.