

TECHNICAL DATASHEET

SAP No. 30004044 Article Description U-C-603g/m²-1230mm

Textile Structure 7003743 SAERTEX[®]

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

| Layer | Construction | Areal weight | Tolerance | Material |
|-----------|--------------|----------------------|------------------------|----------------------------|
| 3 | 0 ° | 581 g/m ² | +/- 5,0 % | ZOLTEK PANEX 35-13 50K |
| 2 | -60 ° | 8 g/m ² | +/- 5,0 % | E-glass 68 TEX |
| 1 | 60 ° | 8 g/m ² | +/- 5,0 % | E-glass 68 TEX |
| Stitching | | 6 g/m ² | +/- 1 g/m ² | PES [Polyester] 74 dtex SC |

FURTHER CHARACTERISTICS

| | | | | | |
|---------------|---------|-------------------|-----------|--------------------|----------------------|
| Gauge | 5,0 | Stitching pattern | tricot | Width (nominal) | 1.230 mm |
| Stitch length | 3,00 mm | Total tolerance | +/- 5,1 % | Total areal weight | 603 g/m ² |

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage With original packaging: No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.