

TECHNICAL DATASHEET

SAP No. 30007510 Article Description U-E-640g/m²-1260mm

Textile Structure 7004118 SAERTEX[®]

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

| Layer | Construction | Areal weight | Tolerance | Material |
|-----------|--------------|----------------------|------------------------|-----------|
| 4 | 0 ° | 567 g/m ² | +/- 5,0 % | E-glass |
| 3 | 45 ° | 13 g/m ² | +/- 5,0 % | E-glass |
| 2 | 90 ° | 35 g/m ² | +/- 5,0 % | E-glass |
| 1 | -45 ° | 13 g/m ² | +/- 5,0 % | E-glass |
| Stitching | | 12 g/m ² | +/- 3 g/m ² | synthetic |

Fiber input can be determined individually

FURTHER CHARACTERISTICS

| | | | | | |
|---------------|---------|-------------------|-----------|--------------------|----------------------|
| Gauge | 10,0 | Stitching pattern | tricot | Width (nominal) | 1260 mm |
| Stitch length | 3,00 mm | Total tolerance | +/- 5,4 % | Total areal weight | 640 g/m ² |

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage With original packaging: No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.