

TECHNICAL DATASHEET

SAP No. 30007788 Article Description SAERcore B 200/PP18/200 - 1250mm

Textile Structure 7006259 SAERcore®

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
3	CSM	200 g/m ²	+/- 10,0 %	E-glass
2	Core	180 g/m ²	+/- 10,0 %	Polypropylen
1	CSM	200 g/m ²	+/- 10,0 %	E-glass
Stitching		7 g/m ²	+/- 2 g/m ²	Polyamid 6.6 122 dtex

Fiber input can be determined individually

FURTHER CHARACTERISTICS

Gauge	3,5	Stitching pattern	tricot	Width (nominal)	1250 mm
Stitch length	5,00 mm	Total tolerance	+/- 10,2 %	Total areal weight	587 g/m ²

Labelling (Standard)	Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.
Packaging (Standard)	Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.
Storage	With original packaging: No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.
Important advice	The Z side of the stitching line should be place preferably on the cosmetic face to obtain the best surface finish.