

TECHNICAL DATASHEET

SAP No. 30005744 Article Description X-C-603g/m²-1400mm

Textile Structure 7003884 SAERTow®

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
2	-45 °	300 g/m ²	+/- 5,0 %	ZOLTEK PANEX 35-13 50K -
1	45 °	300 g/m ²	+/- 5,0 %	ZOLTEK PANEX 35-13 50K -
Stitching		3 g/m ²	+/- 1 g/m ²	PES [Polyester] 33 dtex SC

FURTHER CHARACTERISTICS

Gauge	5,0	Stitching pattern	warp	Width (nominal)	1.400 mm
Stitch length	2,60 mm	Total tolerance	5,1 %	Total areal weight	603 g/m ²

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage recommendation With original packaging: Temperature 15-35°C and 20-80% humidity. No moisture and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.