

TECHNICAL DATASHEET

SAP No. 30007553 Article Description SAERflow CSM150/BX304 445g/m²-1270mm
Textile Structure 7007999 SAERTEX[®]

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
5	CSM	150 g/m ²	+/- 10,0 %	E-glass
4	0 °	10 g/m ²	+/- 5,0 %	E-glass 34 TEX
3	45 °	134 g/m ²	+/- 5,0 %	- Synthetic 380 TEX
2	0 °	10 g/m ²	+/- 5,0 %	E-glass 34 TEX
1	45 °	134 g/m ²	+/- 5,0 %	- Synthetic 380 TEX
Stitching		7 g/m ²	+/- 2 g/m ²	Polyamide 6.6 122 dtex

Fiber input can be determined individually

FURTHER CHARACTERISTICS

Gauge	3,5	Stitching pattern	tricot	Width (nominal)	1270 mm
Stitch length	4,00 mm	Total tolerance	+/- 7,1 %	Total areal weight	445 g/m ²

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage With original packaging: No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.