

TECHNICAL DATASHEET

SAP No. SAERcore 300/RC18/300 - 1250mm 30016221 Article Description

Textile Structure 7011059 SAERcore®

| ARTICLE CONSTRUCTION (in accordance with EN 13473-1) | | | | | | | | | |
|--|--------------|--------------|------------|-------------------------|--|--|--|--|--|
| Layer | Construction | Areal weight | Tolerance | Material | | | | | |
| 3 | CSM | 300 g/m² | +/- 10,0 % | E-glass | | | | | |
| 2 | Core | 180 g/m² | +/- 10,0 % | Recycled Synthetic Core | | | | | |
| 1 | CSM | 300 g/m² | +/- 10,0 % | E-glass | | | | | |
| Stitching | | 7 g/m² | +/- 2 g/m² | Polyamid 6.6 122 dtex | | | | | |

Fiber input can be determined individually

| FURTHER CHARACTERISTICS | | | | | | | | | |
|-------------------------|---------|--|------------|--------------------|----------|--|--|--|--|
| Gauge | 3,5 | Stitching pattern | tricot | Width (nominal) | 1250 mm | | | | |
| Stitch length | 5,00 mm | Total tolerance | +/- 10,2 % | Total areal weight | 787 g/m² | | | | |
| Labelling (Standard) | | Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box. | | | | | | | |

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage Keep in original packaging. Store in a dry environment. Avoid direct sunlight. Fabrics to be kept under processing conditions at least 24 hours (recommendation)

prior to use to avoid problems with humidity and electrostatic charge.

The Z side of the stitching line should be place preferably on the cosmetic Important advice

face to obtain the best surface finish.