

## TECHNICAL DATASHEET

SAP No. 30000345 Article Description Y-E-625g/m<sup>2</sup>-1270mm

Textile Structure 7000173 SAERTEX®

### ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
3	0 °	213 g/m <sup>2</sup>	+/- 5 %	E-glass 600 TEX
2	45 °	200 g/m <sup>2</sup>	+/- 5 %	E-glass 300 TEX
1	-45 °	200 g/m <sup>2</sup>	+/- 5 %	E-glass 300 TEX
Stitching		12 g/m <sup>2</sup>	+/- 3 g/m <sup>2</sup>	PES [Polyester] 76 dtex

Fiber input can be determined individually

### FURTHER CHARACTERISTICS

Gauge	10,0	Stitching pattern	tricot-warp	Width (nominal)	1.270 mm
Stitch length	2,60 mm	Total tolerance	5,4 %	Total areal weight	625 g/m <sup>2</sup>

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage recommendation With original packaging: Temperature 15-35°C and 20-80% humidity. No moisture and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.