

TECHNICAL DATASHEET

| SAP No. | 30007904 | Article Description B-C- | 306g/m²-1270m | m | |
|--|-----------|---|---------------|-------------------------|----------|
| Textile Structure 7007924 SAERTEX® | | | | | |
| ARTICLE CONSTRUCTION (in accordance with EN 13473-1) | | | | | |
| Layer | Construct | tion Areal weight | Tolerance | Material | |
| 2 | 0 ° | 150 g/m² | +/- 5,0 % | ZOLTEK PANEX 35-13 50 | ΙK |
| 1 | 90 ° | 150 g/m² | +/- 5,0 % | ZOLTEK PANEX 35-13 50 | K |
| Stitching | | 6 g/m² | +/- 1 g/m² | PES [Polyester] 76 dtex | |
| FURTHER CHARACTERISTICS | | | | | |
| Gauge | 5,0 | Stitching pattern tric | ot | Width (nominal) | 1270 mm |
| Stitch length | 2,60 mm | Total tolerance +/- | 5,2 % | Total areal weight | 306 g/m² |
| Labelling (Standard) | | Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box. | | | |
| Packaging (Standard) | | Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually. | | | |
| Storage | | With original packaging: No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions. | | | |

