

TECHNICAL DATASHEET

SAP No. 30005821 Article Description X-C-302g/m²-1400mm

Textile Structure 7006087 SAERTow®

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
2	-45 °	149 g/m ²	+/- 5,0 %	TORAY T700SC 50C 12K
1	45 °	149 g/m ²	+/- 5,0 %	TORAY T700SC 50C 12K
Stitching		4 g/m ²	+/- 1 g/m ²	PES [Polyester] 48 dtex SC

FURTHER CHARACTERISTICS

Gauge	5,0	Stitching pattern	warp	Width (nominal)	1.400 mm
Stitch length	2,60 mm	Total tolerance	+/- 5,3 %	Total areal weight	302 g/m ²

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage With original packaging: No moisture recommendationn and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.