



TECHNICAL DATASHEET

SAP No. 30010084 Article Description B-S-E-1089g/m²-1270mm / E-LT 2408
Textile Structure 7008501 SAERTEX®

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
3	0 °	425 g/m ² 12.54 oz/yd ²	+/- 5.0 %	E-glass 1,200 TEX
2	90 °	402 g/m ² 11.86 oz/yd ²	+/- 5.0 %	E-glass 1,200 TEX
1	CSM	250 g/m ² 7.37 oz/yd ²	+/- 10.0 %	Boron free glass
Stitching		12 g/m ² 0.35 oz/yd ²	+/-3 g/m ² +/-0.09 oz/yd ²	PES [Polyester] 110 dtex

Fiber input can be determined individually

FURTHER CHARACTERISTICS

Gauge	7.0	Stitching pattern	tricot-warp	Width (nominal)	1270 mm
Stitch length	4.00 mm	Total tolerance	6.4 %	Total areal weight	1089 g/m ² 32.1 oz/yd ²

Labelling (Standard)	Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.
Packaging (Standard)	Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.
Storage (recommendation)	Keep in original packaging. Store in a dry environment. Avoid direct sunlight. Fabrics to be kept under processing conditions at least 24 hours prior to use to avoid problems with humidity and electrostatic charge.