

TECHNICAL DATASHEET

SAP No. 30017115 Article Description X-S-E-662g/m²-1270mm

Textile Structure 7011464 SAERTEX®

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
5	CSM	250 g/m ² 7.37 oz/yd ²	+/- 10.0 %	Boron free glass
4	45 °	200 g/m ² 5.90 oz/yd ²	+/- 5.0 %	E-glass 300 TEX
3	90 °	3 g/m ² 0.09 oz/yd ²	+/- 5.0 %	E-glass 68 TEX
2	0 °	3 g/m ² 0.09 oz/yd ²	+/- 5.0 %	E-glass 68 TEX
1	-45 °	200 g/m ² 5.90 oz/yd ²	+/- 5.0 %	E-glass 300 TEX
Stitching		6 g/m ² 0.18 oz/yd ²	+/- 1 g/m ² +/- 0.03 oz/yd ²	PES [Polyester] 76 dtex

Fiber input can be determined individually

FURTHER CHARACTERISTICS

Gauge	5.0	Stitching pattern	tricot	Width (nominal)	1270 mm
Stitch length	2.60 mm	Total tolerance	7.0 %	Total areal weight	662 g/m ² 19.5 oz/yd ²

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage (recommendation) Keep in original packaging. Store in a dry environment. Avoid direct sunlight. Fabrics to be kept under processing conditions at least 24 hours prior to use to avoid problems with humidity and electrostatic charge.