

TECHNICAL DATASHEET

SAP No. 30017119 Article Description Q-E-1635g/m²-1270mm

Textile Structure 7011468 SAERTEX®

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
4	0 °	425 g/m ²	+/- 5.0 %	E-glass 1,200 TEX
3	45 °	401 g/m ²	+/- 5.0 %	E-glass 600 TEX
2	90 °	402 g/m ²	+/- 5.0 %	E-glass 1,200 TEX
1	-45 °	401 g/m ²	+/- 5.0 %	E-glass 600 TEX
Stitching		6 g/m ²	+/- 1 g/m ²	PES [Polyester] 76 dtex

Fiber input can be determined individually

FURTHER CHARACTERISTICS

Gauge	5.0	Stitching pattern	tricot-warp	Width (nominal)	1270 mm
Stitch length	3.00 mm	Total tolerance	5.0 %	Total areal weight	1635 g/m ²

Labelling (Standard)	Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.
Packaging (Standard)	Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.
Storage (recommendation)	Keep in original packaging. Store in a dry environment. Avoid direct sunlight. Fabrics to be kept under processing conditions at least 24 hours prior to use to avoid problems with humidity and electrostatic charge.