

TECHNICAL DATASHEET

SAP No. 30017120 Article Description Q-S-E-1496g/m²-1270mm

Textile Structure 7011463 SAERTEX®

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
5	0 °	331 g/m ²	+/- 5.0 %	E-glass 1,200 TEX
4	45 °	301 g/m ²	+/- 5.0 %	E-glass 600 TEX
3	90 °	307 g/m ²	+/- 5.0 %	E-glass 600 TEX
2	-45 °	301 g/m ²	+/- 5.0 %	E-glass 600 TEX
1	CSM	250 g/m ²	+/- 10.0 %	Boron free glass

Stitching 6 g/m² +/- 1 g/m² PES [Polyester] 76 dtex

Fiber input can be determined individually

FURTHER CHARACTERISTICS

Gauge	5.0	Stitching pattern	tricot-warp	Width (nominal)	1270 mm
Stitch length	3.00 mm	Total tolerance	5.9 %	Total areal weight	1496 g/m ²

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage (recommendation) Keep in original packaging. Store in a dry environment. Avoid direct sunlight. Fabrics to be kept under processing conditions at least 24 hours prior to use to avoid problems with humidity and electrostatic charge.