



TECHNICAL DATASHEET

SAP No. 30017452 Article Description Q-C-632g/m²-1270mm / C-QX 1800
Textile Structure 7010988 SAERTEX®

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
4	0 °	157 g/m ² 4.63 oz/yd ²	+/- 5.0 %	HYOSUNG H2550 A-Size 12K
3	45 °	156 g/m ² 4.60 oz/yd ²	+/- 5.0 %	HYOSUNG H2550 A-Size 12K
2	90 °	157 g/m ² 4.63 oz/yd ²	+/- 5.0 %	HYOSUNG H2550 A-Size 12K
1	-45 °	156 g/m ² 4.60 oz/yd ²	+/- 5.0 %	HYOSUNG H2550 A-Size 12K
Stitching		6 g/m ² 0.18 oz/yd ²	+/-1 g/m ² +/-0.03 oz/yd ²	PES [Polyester] 76 dtex

FURTHER CHARACTERISTICS

Gauge	5.00	Stitching pattern	tricot-warp	Width (nominal)	1270 mm
Stitch length	2.70 mm	Total tolerance	5.1 %	Total areal weight	632 g/m ² 18.6 oz/yd ²

Labelling (Standard)	Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.
Packaging (Standard)	Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.
Storage (recommendation)	Keep in original packaging. Store in a dry environment. Avoid direct sunlight. Fabrics to be kept under processing conditions at least 24 hours prior to use to avoid problems with humidity and electrostatic charge.