

## TECHNICAL DATASHEET

SAP No. 30000335 Article Description Q-E-635g/m<sup>2</sup>-1270mm

Textile Structure 7000166

SAERTEX®

### ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
5	0 °	59 g/m <sup>2</sup>	+/- 5,0 %	E-glass 300 TEX
4	0 °	118 g/m <sup>2</sup>	+/- 5,0 %	E-glass 600 TEX
3	45 °	156 g/m <sup>2</sup>	+/- 5,0 %	E-glass 200 TEX
2	90 °	134 g/m <sup>2</sup>	+/- 5,0 %	E-glass 200 TEX
1	-45 °	156 g/m <sup>2</sup>	+/- 5,0 %	E-glass 200 TEX
Stitching		12 g/m <sup>2</sup>	+/- 3 g/m <sup>2</sup>	PES [Polyester] 76 dtex

Fiber input can be determined individually

### FURTHER CHARACTERISTICS

Gauge	10,0	Stitching pattern	tricot-warp	Width (nominal)	1270 mm
Stitch length	2,60 mm	Total tolerance	+/- 5,4 %	Total areal weight	635 g/m <sup>2</sup>

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage (recommendation) Keep in original packaging. Store in a dry environment. Avoid direct sunlight. Fabrics to be kept under processing conditions at least 24 hours prior to use to avoid problems with humidity and electrostatic charge.