

TECHNICAL DATASHEET

SAP No. 30000341 Article Description Q-E-986g/m²-1270mm

Textile Structure 7000171 SAERTEX®

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)									
Layer	Construction	Areal weight	Tolerance	Material					
4	0°	236 g/m²	+/- 5,0 %	E-glass 600 TEX					
3	45 °	251 g/m²	+/- 5,0 %	E-glass 300 TEX					
2	90 °	236 g/m²	+/- 5,0 %	E-glass 600 TEX					
1	-45 °	251 g/m²	+/- 5,0 %	E-glass 300 TEX					
Stitching		12 g/m²	+/- 3 g/m²	PES [Polyester] 76 dtex					

Fiber input can be determined individually

FURTHER CHARACTERISTICS									
Gauge	10,0	Stitching pattern	tricot-warp	Width (nominal)	1270 mm				
Stitch length	2,60 mm	Total tolerance	+/- 5,2 %	Total areal weight	986 g/m²				

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on

the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging

options can be determined individually.

Storage Keep in original packaging. Store in a dry environment. Avoid direct sunlight.

(recommendation) Fabrics to be kept under processing conditions at least 24 hours

prior to use to avoid problems with humidity and electrostatic charge.