

## TECHNICAL DATASHEET

SAP No. 30007553 Article Description SAERflow 150/BX304 - 1270mm

Textile Structure 7007999 SAERTEX®

### ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
5	CSM	150 g/m <sup>2</sup>	+/- 10,0 %	E-glass
4	0 °	10 g/m <sup>2</sup>	+/- 5,0 %	E-glass 34 TEX
3	45 °	134 g/m <sup>2</sup>	+/- 5,0 %	- Hybrid Glass 380,00 TEX
2	0 °	10 g/m <sup>2</sup>	+/- 5,0 %	E-glass 34 TEX
1	-45 °	134 g/m <sup>2</sup>	+/- 5,0 %	- Hybrid Glass 380,00 TEX
Stitching		7 g/m <sup>2</sup>	+/- 2 g/m <sup>2</sup>	Polyamide 6.6 122 dtex

Fiber input can be determined individually

### FURTHER CHARACTERISTICS

Gauge	3,5	Stitching pattern	tricot	Width (nominal)	1270 mm
Stitch length	4,00 mm	Total tolerance	+/- 7,1 %	Total areal weight	445 g/m <sup>2</sup>

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage (recommendation) Keep in original packaging. Store in a dry environment. Avoid direct sunlight. Fabrics to be kept under processing conditions at least 24 hours prior to use to avoid problems with humidity and electrostatic charge.