

## **TECHNICAL DATASHEET**

SAP No. 30007632 Article Description X-E-810g/m<sup>2</sup>-1270mm

Textile Structure 7004132 SAERTEX®

| ARTICLE CONSTRUCTION (in accordance with EN 13473-1) |              |              |            |                         |  |  |  |  |  |
|--|--------------|--------------|------------|-------------------------|--|--|--|--|--|
| Layer  | Construction | Areal weight | Tolerance  | Material                |  |  |  |  |  |
| 3  | 45 °         | 401 g/m²     | +/- 5,0 %  | E-glass 600 TEX         |  |  |  |  |  |
| 2  | 0 °          | 2 g/m²       | +/- 5,0 %  | E-glass 68 TEX          |  |  |  |  |  |
| 1  | -45 °        | 401 g/m²     | +/- 5,0 %  | E-glass 600 TEX         |  |  |  |  |  |
| Stitching  |              | 6 g/m²       | +/- 1 g/m² | PES [Polyester] 76 dtex |  |  |  |  |  |

Fiber input can be determined individually

| FURTHER CHARACTERISTICS |         |                   |           |                    |          |  |  |  |  |
|-------------------------|---------|-------------------|-----------|--------------------|----------|--|--|--|--|
| Gauge                   | 5,0     | Stitching pattern | warp      | Width (nominal)    | 1270 mm  |  |  |  |  |
| Stitch length           | 3,00 mm | Total tolerance   | +/- 5,1 % | Total areal weight | 810 g/m² |  |  |  |  |

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on

the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging

options can be determined individually.

Storage Keep in original packaging. Store in a dry environment. Avoid direct sunlight.

(recommendation) Fabrics to be kept under processing conditions at least 24 hours

prior to use to avoid problems with humidity and electrostatic charge.